

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

Please add the following new claims:

21. (New) A method for reducing profile distortion in wafer fabrication without roughening a semiconductor substrate surface, comprising:

providing a semiconductor substrate comprising a film comprising silicon-nitride;  
treating the film in a vacuum of about 3.0-6.5 Torr, for a time of about 10 seconds to about 5 minutes, and in an atmosphere free of argon comprising oxygen plasma as the gas present in the greatest concentration wherein the oxygen plasma flow rate is at least about 300 sccm oxygen and the atmosphere renders the substrate resistant to profile distortion and roughening to make a treated substrate;

applying a resist to the treated substrate; and

patterning the resist.

22. (New) The method of claim 21 and further including exposing oxygen gas to an energy source generating about 150-900 watts in order to make the oxygen plasma.

23. (New) The method of claim 21 wherein the oxygen plasma is made by electromagnetic excitation of oxygen gas by electrodes that are about 400 to 600 mils apart.

24. (New) The method of claim 21 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is RF energy.

25. (New) The method of claim 21 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is microwave energy.

26. (New) The method of claim 21 wherein the reduced profile distortion is footing.

27. (New) The method of claim 21 wherein the reduced profile distortion is undercutting.

BEST AVAILABLE COPY

28. (New) The method of claim 1 and further including removing the resist from the silicon nitride film with reduced profile distortion.
29. (New) The method of claim 21 wherein the oxygen flow rate is not greater than about 2000 sccm.
30. (New) The method of claim 21 and further comprising adding an inert gas to the oxygen gas.
31. (New) A method for reducing profile distortion in substrate fabrication without roughening a semiconductor substrate surface, comprising:  
    providing a semiconductor substrate comprising a film comprising silicon-nitride;  
    treating the film in a vacuum of about 3.0-6.5 Torr, for a time of about 10 seconds to about 5 minutes, and in an atmosphere free of argon comprising oxygen plasma as the gas present in the greatest concentration wherein the oxygen plasma flow rate is at least about 300 sccm oxygen and the atmosphere renders the substrate resistant to profile distortion and roughening to make a treated substrate;  
    applying a resist to the treated substrate; and  
    patterning the resist
32. (New) The method of claim 31 and further including exposing oxygen gas to an energy source generating about 150-900 watts in order to make the oxygen plasma.
33. (New) The method of claim 31 wherein the oxygen plasma is made by electromagnetic excitation of oxygen gas by electrodes that are about 400 to 600 mils apart.
34. (New) The method of claim 31 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is RF energy.

BEST AVAILABLE COPY

35. (New) The method of claim 31 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is microwave energy.
36. (New) The method of claim 31 wherein the reduced profile distortion is footing.
37. (New) The method of claim 31 wherein the reduced profile distortion is undercutting.
38. (New) The method of claim 31 and further including removing the resist from the silicon nitride film with reduced profile distortion.
39. (New) The method of claim 31 wherein the oxygen flow rate is not greater than about 2000 sccm.
40. (New) The method of claim 31 and further comprising adding an inert gas to the oxygen gas.

BEST AVAILABLE COPY

**CLEAN VERSION OF PENDING CLAIMS**

**OXYGEN PLASMA TREATMENT FOR NITRIDE SURFACE TO REDUCE PHOTO  
FOOTING**

Applicant: Zhiping Yin et al.  
Serial No.: 09/259,762

---

*Claims 1-3 and 5-11 and 21-40, as of December 9, 2002 (Date of Response to First  
Office Action after RCE).*

---

*MUSFI  
E*

1. (Amended) A method for reducing profile distortion in semiconductor fabrication without roughening a semiconductor substrate surface, comprising:  
    providing a semiconductor substrate comprising a film comprising silicon-nitride;  
    treating the film in a vacuum of about 3.0-6.5 Torr, for a time of about 10 seconds to about 5 minutes, and in an atmosphere free of argon comprising oxygen plasma as the gas present in the greatest concentration wherein the oxygen plasma flow rate is at least about 300 sccm oxygen and the atmosphere renders the substrate resistant to profile distortion and roughening to make a treated substrate;  
    applying a resist to the treated substrate; and  
    patterning the resist.

---

2. The method of claim 1 and further including exposing oxygen gas to an energy source generating about 150-900 watts in order to make the oxygen plasma.

3. The method of claim 2 wherein the oxygen plasma is made by electromagnetic excitation of oxygen gas by electrodes that are about 400 to 600 mils apart.

5. The method of claim 2 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is RF energy.

6. The method of claim 2 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is microwave energy.
7. The method of claim 1 wherein the reduced profile distortion is footing.
8. The method of claim 1 wherein the reduced profile distortion is undercutting.
9. The method of claim 1 and further including removing the resist from the silicon nitride film with reduced profile distortion.
10. The method of claim 1 wherein the oxygen flow rate is not greater than about 2000 sccm.
11. The method of claim 1 and further comprising adding an inert gas to the oxygen gas.

- sub F1  
E2
- 
21. (New) A method for reducing profile distortion in wafer fabrication without roughening a semiconductor substrate surface, comprising:
    - providing a semiconductor substrate comprising a film comprising silicon-nitride;
    - treating the film in a vacuum of about 3.0-6.5 Torr, for a time of about 10 seconds to about 5 minutes, and in an atmosphere free of argon comprising oxygen plasma as the gas present in the greatest concentration wherein the oxygen plasma flow rate is at least about 300 sccm oxygen and the atmosphere renders the substrate resistant to profile distortion and roughening to make a treated substrate;
    - applying a resist to the treated substrate; and
    - patterning the resist.
  22. (New) The method of claim 21 and further including exposing oxygen gas to an energy source generating about 150-900 watts in order to make the oxygen plasma.

23. (New) The method of claim 21 wherein the oxygen plasma is made by electromagnetic excitation of oxygen gas by electrodes that are about 400 to 600 mils apart.
24. (New) The method of claim 21 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is RF energy.
25. (New) The method of claim 21 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is microwave energy.
26. (New) The method of claim 21 wherein the reduced profile distortion is footing.
27. (New) The method of claim 21 wherein the reduced profile distortion is undercutting.
28. (New) The method of claim 1 and further including removing the resist from the silicon nitride film with reduced profile distortion.
29. (New) The method of claim 21 wherein the oxygen flow rate is not greater than about 2000 sccm.
30. (New) The method of claim 21 and further comprising adding an inert gas to the oxygen gas.
31. (New) A method for reducing profile distortion in substrate fabrication without roughening a semiconductor substrate surface, comprising:  
    providing a semiconductor substrate comprising a film comprising silicon-nitride;  
    treating the film in a vacuum of about 3.0-6.5 Torr, for a time of about 10 seconds to about 5 minutes, and in an atmosphere free of argon comprising oxygen plasma as the gas present in the greatest concentration wherein the oxygen plasma flow rate is at least about 300

E2  
Cont.

sccm oxygen and the atmosphere renders the substrate resistant to profile distortion and roughening to make a treated substrate;

applying a resist to the treated substrate; and  
patterning the resist

32. (New) The method of claim 31 and further including exposing oxygen gas to an energy source generating about 150-900 watts in order to make the oxygen plasma.

33. (New) The method of claim 31 wherein the oxygen plasma is made by electromagnetic excitation of oxygen gas by electrodes that are about 400 to 600 mils apart.

34. (New) The method of claim 31 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is RF energy.

E2  
cont.  
35. (New) The method of claim 31 wherein the oxygen plasma is made by an exposure of oxygen gas to an energy source that is microwave energy.

36. (New) The method of claim 31 wherein the reduced profile distortion is footing.

37. (New) The method of claim 31 wherein the reduced profile distortion is undercutting.

38. (New) The method of claim 31 and further including removing the resist from the silicon nitride film with reduced profile distortion.

39. (New) The method of claim 31 wherein the oxygen flow rate is not greater than about 2000 sccm.



Clean Version of Pending Claims  
U.S. Serial No. 09/259,762  
303.531US1

Page 2

40. (New) The method of claim 31 and further comprising adding an inert gas to the oxygen gas.

---

E2